



# Celmend Steel

## Product Information

### Description

**Celmend Steel** is a non-rusting steel reinforced epoxy putty used to provide fast, permanent repairs to items made of ferrous metal. It will repair holes, cracks and threads in castings, pipes and tools, and can be used to hold fixtures and signs, to make models and prototypes, to form nuts in situ and to lock threads. Celmend Steel is a hand kneadable epoxy putty supplied as a two-part concentric stick of contrasting colours; when mixed it sets to a hard, dark grey material which can be drilled, tapped, machined or filed as required.

### Directions of use

1. In order to achieve optimum adhesion, surfaces should be cleaned free of grease, dirt, paint etc., and preferably should be dry. To ensure a good bond, abrade both surfaces followed by additional cleaning.
2. Twist or cut off the required amount of Celmend Steel.
3. If the material is cold mixing may be difficult, and warming to room temperature is advised.
4. To mix, knead the putty with the fingers for at least one minute or until it is a uniform colour.
5. Press the putty onto the prepared surface within 2 minutes of mixing.
- 6.1. If it is being used as an adhesive, force some putty against each of the two surfaces to be joined, before pressing the faces together, and support the joint as necessary.
- 6.2. If it is being used as a filler/repair material force the putty into the area to be filled, and shape and strike off any excess with a tool wetted with clean water.
7. For a smooth appearance rub with water or a damp cloth within the working life of the putty.
8. After 5-10 minutes the epoxy putty will harden like metal and start to form a bond. After 60 minutes the material will be cured sufficiently to allow a repaired water system to be put back into service. Full cure will be achieved after 24 hours.

### Packaging

Celmend Steel is supplied in a stick form wrapped in a clear release film. The stick has a nominal 22mm diameter and is available in various lengths. Packaged in a reusable clear plastic tube with a plastic friction top.

### Shelf Life

Celmend Steel should be stored out of direct sunlight in dry frost free conditions of temperatures between 5° and 20°C. Under such conditions shelf life will be 18 months from the date of manufacture. One year minimum from date of shipment when stored in original, unopened container in a dry area at temperatures below 75°F (24°C).

### Technical Data

Work life	3 minutes @ 20°C
Shore D Hardness	80
Lap shear strength on steel	6.2N/mm <sup>2</sup>
Temperature Limitations	120°C continuous 150°C intermittent
Electrical resistance	30,000 MΩ
Dielectric Strength	300 V/mm
Compressive Strength	80N/mm <sup>2</sup>
<b>Chemical resistance:</b> Resistant to hydrocarbons, ketones, alcohols, esters, halocarbons, aqueous salt solutions, dilute acids and bases.	

\*Typical properties are for information only, not for purposes of specification. The data above represents product performance in ideal laboratory conditions. Individual users' experience may vary depending on application conditions.



### Important Note

Whilst all reasonable care is taken in compiling technical data on the Company's products, all recommendations or suggestions regarding the use of such products are made without guarantee, since the conditions of use are beyond the control of the Company. It is the customer's responsibility to satisfy himself that each product is fit for the purpose for which he intends to use it, that the actual conditions of use are suitable and that in the light of our continual research and development programme the information relating to each product has not been superseded.



#### **2K Polymer Systems Limited**

Venture Crescent, Alfreton  
Derbyshire DE55 7RA  
United Kingdom

Tel: +44 (0) 1773 540440  
Fax: +44 (0) 1773 607638  
Email: [info@2kps.net](mailto:info@2kps.net)  
Website: [www.2kps.net](http://www.2kps.net)

#### **2K Polymer Systems, Inc.**

10325 State Route 43, Suite N  
Streetsboro, Ohio 44241  
United States of America

Tel: 330-562-0816  
Fax: 330-562-2657  
Email: [info@2kps.net](mailto:info@2kps.net)  
Website: [www.2kps.net](http://www.2kps.net)

#### **2K Polymer Systems Pte. Limited**

6 Shenton Way  
#39-02 OUE Downtown 1  
Singapore 068809

Email: [info@2kps.net](mailto:info@2kps.net)  
Website: [www.2kps.net](http://www.2kps.net)